





## Pilkington **Optifloat™** Opal

### The new translucent glass that's easier to handle

Whilst they can look stunning and create a beautiful effect, many translucent glass types on the market have proved difficult to stock, handle and process – until now.

Pilkington **Optifloat™** Opal offers all the diffused natural light of a translucent glass, but with none of the drawbacks. An acid-etched product suitable for internal or external use, it creates an attractive finish for windows, partition walls, glass doors, furniture, shelving, wall cladding and many more applications. But the real beauty is that it can be stored and processed in the same way as standard float glass, is readily available from stock in a range of thicknesses and can be easily toughened, laminated or brilliant cut – making Pilkington **Optifloat™** Opal the ideal choice.

#### Features:

- Acid etched glass
- High light transmittance
- Diffuses light to give a uniform natural look
- 'Velvet smooth' and durable surface
- Can be used internally and externally
- Etched surface has low reflection

#### Benefits:

For building occupiers:

- High value in appearance
- Creates excellent privacy whilst allowing light in
- Natural light diffusion

For processors:

- Available from stock
- Can be stored and processed as ordinary float glass
- Easily toughened, laminated and brilliant cut
- Readily available in 4 mm and 6 mm
- Standard stock size 3210×2250 mm
- Thicknesses of 8 mm, 10 mm and other stock sizes available on request

#### Applications:

- Windows
- Partition walls
- Glass doors
- Glass furniture
- Doors
- Display cases
- Shelves and cabinets
- Working surfaces
- Wall cladding
- Balustrades

#### Performance Table

Glass product	Light transmittance (%)	Light reflectance (%)	Direct transmittance (%)	Reflectance (%)	Absorptance (%)	Total solar heat transmittance (%)	TSC	U <sub>g</sub> -value [W/m <sup>2</sup> K]
4 mm Pilkington <b>Optifloat™</b> Opal	83	8	78	7	15	82	0.94	5.8
6 mm Pilkington <b>Optifloat™</b> Opal	83	8	75	7	18	80	0.92	5.7
4 mm Pilkington <b>K Glass™</b> / 16 mm / 4 mm Pilkington <b>Optifloat™</b> Opal	74	16	60	14	26	67	0.77	1.5
6 mm Pilkington <b>K Glass™</b> / 16 mm / 6 mm Pilkington <b>Optifloat™</b> Opal	72	16	56	13	31	64	0.74	1.5

U<sub>g</sub>-values for single glass or with 90% argon fill for insulating glass units. For single glass the treated surface faces the room and for IGUs the treated surface faces the cavity. Rotating the IGU will change the overall performance, please contact us for the relevant data. All performance data has been determined in accordance with EN 410 and EN 673.

To the fullest extent permitted by applicable laws, Nippon Sheet Glass Co. Ltd. and its subsidiary companies disclaim all liability for any error in or omission from this publication and for all consequences of relying on it.



#### Pilkington Group Limited

European Technical Centre

Hall Lane – Lathom Nr Ormskirk L40 5UF – United Kingdom

marketing.communications@nsg.com

[www.pilkington.com](http://www.pilkington.com)